

Approximate Composition of recalibration sample no. 105, 15, 115, low alloy steel,  
Sample type: Chart Control Sample  
Belec Ref.: 105 recalRN0504EN.  
Sample size approx.. 37 mm Dia. x 17 mm Thickness

**Composition:**  
given in %

C	Carbon.....	0,49	Nb	Niobium	
Si	Silicon.....	0.219	Pb	Lead / Plumb.....	0,259
Mn	Manganese.....	0,73	Sn	Tin / Stanium	
P	Phosphor.....	0,005	Ti	Titanium	
S	Sulfur.....	0,025	V	Vanadium	
Cr	Chromium.....	0,050	W	Tungsten	
Mo	Molybdenum.....	0,023	Mg	Magnesium	
Ni	Nickel.....	0,129	Ce	Cerium	
Al	Aluminium		La	Lanthanium	
As	Arsenic		Ta	Tantalum	
B	Boron		Te	Tellurium	
Co	Cobalt		Bi	Bismuth	
Cu	Copper		N	Nitrogen	